



Cold applied, easy to mix asphalt repair.  
 Cures at colder temps. vs. traditional materials.  
 100% solids polymer composite.  
 No water or solvents.

## WHERE TO USE

Alligator cracking  
 Potholes

## FEATURES & BENEFITS

**Easy to Apply**  
 Doesn't freeze. Apply as low as 35°F (2°C).  
 No thickness limit. Easily pour 2 in. (5 cm) depth per layer.

**Open to Traffic Fast**  
 100% reactive ingredient mix. No water or solvents.

## Packaging

0.5 ft<sup>3</sup> (15L) Kit

## Color

Black

## Shelf Life

1 year when properly stored

## Storage

Store and ship in dry, low humidity, shaded or covered 50-90°F (10-32°C) environment.

## Safety

Before handling, familiarize yourself with the SDS regarding risks and safe use of this product. Call 800-333-9826 or email [msds@wilvaco.com](mailto:msds@wilvaco.com) to obtain an SDS.

## Application

For instructions for how to handle and apply, refer to: [FastPatch Alligator Crack Repair Kit](#). For details on substrate preparation and examples of cracking patterns, refer to: [FastPatch Alligator Crack Repair Kit Guidelines](#).

## TYPICAL PROPERTIES

**Adhesion to asphalt, ASTM D7234 unprimed | 500 psi (3.45 MPa)\***

*\*100% asphalt failure mode, adhesion limited by substrate quality*

**VOC, ASTM D2369 | 0 lbs/gal (0 g/L)**

**Abrasion, ASTM D4060, 1kg H-18 | 0.2 g loss per 1,000 cycles**

**Service Temperature | -40 to 140°F (-40 to 60°C)**

**Kit Temp. 40°F (4°C) 77°F (25°C) 104°F (40°C)**

Working Time, minutes	18-20	10-12	4-5
Tack Free Time, minutes	90	40	15

## ESTIMATED COVERAGE

	<u>Repair Area</u>	<u>Repair depth</u>	<u>Cracking Pattern</u>	<u>Kits used</u>	<u>Volume</u>
A.	10 ft <sup>2</sup>	0.5-0.75 in. (1-2 cm)	high	1	0.5 ft <sup>3</sup> (19 L)
B.	115 ft <sup>2</sup>	<0.5 in. (<1.3 cm)	medium	3	1.5 ft <sup>3</sup> (42 L)

