

FastPatch DPR Results

Description	Test Method	FastPatch DPR
Part Number:	WVCO	1026212-KIT
Lot #:	WVCO	437276/448038
Gel Time, 70°F	ASTM C881	9:00
Hardness	ASTM D2240	90, 45
Elongation at Break, Overnight cure 70°C	ASTM D412	90 ± 20
Ultimate Tensile Strength, Overnight cure 70°C	ASTM D412	1700 ± 300
Maximum Compressive Stress, Method C, 7 day cure ambient	ASTM C579	1500 ± 300
Maximum Compressive Stress, Method B, 24 hr cure ambient	ASTM C579	1340 ± 30
Maximum Compressive Stress, Method B, 7 day cure ambient	ASTM C579	1740 ± 50
Flexural Strength, 7 day ambient cure	ASTM C580	520 ± 20
Impact Resistance, 7 day cure ambient, Tup FB, (room temp, -20°F)	ASTM D5628	>120, 28.1