

Primer LV



Low Viscosity Primer

Description

POLYQuik® Primer LV is a 2-component, low-viscosity, penetrating urethane primer. POLYQuik® Primer LV is designed for easy application at a wide range of temperatures and fast recoat times. POLYQuik® Primer LV can be applied by airless sprayer or brush/roller.

Applications

- Concrete

Features/Benefits

- **Rapid cure** - 20 minute recoat time at 70°F (21°C)
- **Low viscosity** - great surface wetting & penetration
- **Compatible with all POLYQuik® top coats**
- **Green concrete application** – can be applied on concrete as early as 7 days
- **Applies easily from 40-100°F (4-38°C)**
- **Made in America**

Typical Properties

Description	Result	Method
Solids content	96.4	ATSM D2369
Concrete adhesion	≥450 psi (3.1 MPa)	ATSM D7234

Processing Parameters

Ratio by volume resin : iso	1 to 1
Substrate application temperature	40 to 110° F (10 to 43° C)
Recommended application thickness	Less than 5 mils (0.13 mm)
Application method on horizontal or vertical	Brush/roll or airless spray

Color

Clear/tan

Packaging

10 Gallon Kits - 5 gallons A + 5 gallons B

Shelf life

1 year at recommended storage conditions.

Storage

Store and ship this product in a clean, dry, low-humidity, shaded or covered environment at 60 to 90° F (15 to 32° C).

Document ID: W07-R&D-TDS-340 REV_0 October 2024



■ Recoat Times & Coverage

Because POLYQuik® Primer LV has excellent wetting and soaks into the concrete surface, tack-free time is not a good indicator for recoat time. WVCO/POLYQuik® R&D has measured the minimum recoat time with adhesion strength testing according to ASTM D7234. Below are the results:

Ambient & substrate temperature	Minimum recoat time
95°F (35°C)	10 minutes
70°F (21°C)	20 minutes
40°F (4°C)	30 minutes

Estimated coverage is based on a single coat of brush-applied POLYQuik® Primer LV on concrete substrate as observed during actual repairs in the field. Below is a Coverage Chart:

Volume of mixed material	Coverage Area
½-gallon (1.9-liter)	96 ft² (8.9 m²)
1-gallon (3.8-liter)	192 ft² (18 m²)
2-gallon (7.6-liter)	384 ft² (35 m²)

■ Health & Safety

Before handling, you should become familiar with Safety Data Sheet regarding the risks and safe use of this product. To obtain an SDS please email PolyQuik@wilvaco.com

■ Disclaimer of Warranty

Test results are to be considered as representative of current production and should not be treated as specifications. While all the information presented in this document is believed to be reliable and to represent the best available data on these products, no guarantee, warranty, or representation is made, intended, or implied as to the correctness or sufficiency of any information, or as to the suitability of any chemical compounds for any particular use, or that any chemical compounds or use thereof are not subject to a claim by a third party for infringement of any patent or other intellectual property right. Each user should conduct a sufficient investigation to establish the suitability of any product for its intended use. Proper application is the responsibility of the user. As with any product, the use of this product in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability. Testing is the requirement of both engineers and contractors alike. WVCO does not warrant the application under any or all circumstances.